

CLASSIC SELECT WOODSTAIN

Dulux Trade Classic Select Woodstain protects and decorates exterior smooth planed wood and rough sawn timber. This solvent-based woodstain is deep-penetrating and provides a low build matt finish which will not blister or flake. It offers protection for up to four years if used in accordance with instructions, and is suitable for hardwoods and softwoods.

KEY BENEFITS

- 4 Years Protection
- Cladding & Fascia
- Solvent-Based

PRODUCT INFORMATION

Typical Use

For use on hardwoods and softwoods. In common with other low-build woodstains, **Dulux Trade** Classic Select Woodstain is not recommended for areas of severe exposure and will require more frequent maintenance than a medium build woodstain.

Pack Size

1L, 2.5L and 5L.

Colour Range

See appropriate **Dulux Trade** colour literature, or visit duluxtrade.co.uk.

Film Thickness

Film thickness will be dependent on the coverage achieved. A nominal figure at 14m² per litre will give a wet film thickness of 71 microns.

Composition (nominal)

Pigment: Special Transparent Iron Oxide Micro Pigments and Organic Pigments.

Binder: Alkyd and a Fungicide, for the purpose of protecting the film.

Solvent: Low Odour Aliphatic Hydrocarbons.

Volume Solids

16% (nominal), colours will vary.

SURFACE PREPARATION

To get the best results, ensure surfaces to be stained are sound, clean, dry and free from all

defective or poorly adhering material such as dirt, grease and wax. Surfaces that have been previously painted or varnished must be stripped back to bare wood. All surfaces should be thoroughly rubbed down using a suitable abrasive paper (working in the direction of the grain) and then dusted off (refer to you COSHH Assessment). Special precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead. All screws, nails and other fixings must be non-ferrous.

Where a low-build woodstain has been used on the exterior of joinery and has eroded and weathered and the wood is split, remove defective coatings, glazing materials and beading. Remove any mould, algae, lichen or moss and then treat the surface with **Weathershield** Multi-Surface Fungicidal Wash*. Clean all rebates and rub down all surfaces in the direction of the grain and dust off. Do not use linseed oil putty for glazing (or making good) with natural wood finishes – use external beads set in an appropriate non-setting mastic or a special glazing compound.

It is essential to apply a first coat to the back of cladding and the edges of window frames before fixing into the building etc. Ensure that all areas such as endgrain, top and bottom edges of doors, undersides of sills all receive a liberal coat. For best results use only on joinery manufactured in accordance with BS EN 942: 1996 parts 1&2 (or as amended) 'Quality of Timber and Workmanship in Joinery'. Failure to prepare the surface as described above or apply the recommended number of coats will impair the performance of the system and lead to premature failure or maintenance.

SYSTEMS INFORMATION

STIR THOROUGHLY BEFORE USE. Do not thin. Apply 2 or 3 coats of **Dulux Trade** Classic Select Woodstain.

A factory applied preservative pretreatment is recommended for softwood and non-durable hardwoods. If in doubt, 2 coats of **Weathershield**



CLASSIC SELECT WOODSTAIN

609

Aquatech Preservative Basecoat^{+(BP)**} can be applied to bare exterior wood.

To optimise the dimensional stability, water repellency and durability on exterior joinery, particularly in areas of severe exposure, the use of **Dulux Trade** Protective Woodsheen or **Weathershield** Ultimate Woodstain from **Dulux Trade** is recommended.

For best colour consistency, purchase sufficient tinted paint for each job including touch-in at one time from the same source.

APPLICATION METHOD

Brush only. For Health & Safety reasons relating to all solvent-based products, spray application is not recommended.

As with all solvent-based paints (according to British Standard BS 6150), do not apply in temperatures below 5°C.

Practical Coverage

On surfaces of average porosity, this stain will cover up to 14m² coverage per litre. The figure will vary greatly depending on the porosity of the wood.

Thinning

Do not thin this product.

FURTHER SUPPORT

If you need further support, please contact the **AkzoNobel** Technical Advice Centre on [0333 222 70 70](tel:0333 222 70 70).

***Weathershield** Multi-Surface Fungicidal Wash contains: Benzalkonium Chloride.

****Weathershield Aquatech** Preservative Basecoat^{+(BP)} contains: Dichlofluanid.

Use biocides safely. Always read the label and product information before use.

Always read full Health, Safety & Environmental Information on can before use.

Safety datasheet (SDS 609) is available free on request by telephoning the **AkzoNobel** Technical Advice Centre or by visiting duluxtrade.co.uk.

AkzoNobel, the AkzoNobel logo, the Flourish logo, Dulux Trade, Weathershield, Aquatech and the Planet Possible logo are trademarks of the AkzoNobel group. © AkzoNobel 2014.

Spray Recommendations

This product should not be sprayed.

Drying Times

Single coat at standard thickness:

Touch Dry: 4-6 hours.

Recoat: 16 hours.

Cleaning Up

After use, remove as much woodstain as possible from brushes before cleaning with brush cleaner.

Do not use or store in extremes of temperature.

When this paint container is empty please ask your stockist about recycling. If you have leftover paint, please dispose of it responsibly. Find out more at duluxtrade.co.uk/pp.

Transportation & Storage

Do not use or store in extremes of temperature and protect from frost. To prevent spillage, please store and transport upright.

VOC

EU limit value for this product (cat.: A/f) : 700g/l (2010). This product contains max. 699g/l VOC. VOC Content: Very High (more than 50%).



At **Dulux Trade**, we believe by working with our customers we can reduce waste and do more with the resources we have. Together we can create a better future for our planet. Join us at duluxtrade.co.uk/pp

AkzoNobel