

#### **Technical Data Sheet**

### **Cetol HLS plus**

**Standard** 

Acotint SB translucent

**Description** 

Translucent, solvent-borne alkyd-emulsion based, low-build satin basecoat and wood stain for exterior use.

**GENERAL** 

Main properties / USPs

Resists UV-light, surface mould and algae, peeling and cracking;

The wood grain remains visible and beautifies the wood species;

Microporous, giving a moisture control system;

Provides superior timber protection;

Simple maintenance;

Use

As a primer and one-product application in translucent systems for dimension stable and semi-stable constructions made from new softwood, hardwood, plywood, block board and particle board, such as claddings, fascias, architraves, timber frames, fences and sheds.

Its properties make Cetol HLS plus eminently suitable for application to softwood.

#### **PROPERTIES**

Gloss

Semi-gloss, approximately 30 – 40 GU/60° (ASTM D523)

Colour

Available in the Cetol Design concept

The final colour (or shade) of the Cetol HLS plus system greatly depends on the wood species to which it is applied and any previous coating.

**Density** 

Approx.: 0,905 Kg/dm<sup>3</sup>

Packaging viscosity

Approx. : 24 - 30 seconds, DIN cup 4,  $23^{\circ}$ C

0.4 - 0.7 Pa.s / Cone and Plate / 25°C

**Solids content** 

By weight : Approx. 30 % By volume : Approx. 25-26 %

Volatile Organic Compound

Class A/e; max 500 gr/L (2007) max. 400 g/L (2010)

Cetol HLS plus contains 383 g/L VOC

Drying at 20°C/65% RH

Dust dry: After approx. 4 – 6 hours

Recoatable: After approx. 18 to 24 hours

**Outdoor durability** 

Approximately 2 years for a 3-coat Cetol HLS plus system.

The lighter colors of translucent products are slightly less durable when used outdoors. This is why the low pigmented colors of Cetol HLS plus are based on Base TU, reinforced with UV absorber and HALS. This will result in approximate comparable durability with the other translucent colors of the product.

colors of the product.

Durability greatly depends on location, elevation and by the quality of

wood, design, construction, glazing, condition of interior paint-work, method of application adopted, etc

#### SYSTEM SPECIFICATION

# Timber moisture content New woodwork

Moisture content of timber to be coated should not exceed 16%

Where necessary, apply two coats of Cuprinol ClearWood Preserver on new softwood timber that requires extra substrate protection against fungal attack

Apply a priming coat of Cetol HLS plus for hardwood or softwood in selected color.

Where necessary, repair with a suitable filler such as RepairCare's Dryflex.

Apply 2 finishing coats of Cetol HLS plus.

For best results, it is necessary to keep the interval between applications of these coats limited, not exceeding 1 month.

#### Maintenance

Depending on the condition of the finish, clean, degrease and sand thoroughly.

Repair defects with Cetol HLS plus in the appropriate color and apply one full coat of Cetol HLS plus, overall.

#### **Transparency**

Maintain the translucent appearance of Cetol HLS plus over a longer period. It is recommended to use lighter colors, 077 or 006 for maintenance applications.

# Notes: Covering of horizontal surfaces

During construction, it is recommended to cover horizontal surfaces with plastic to prevent dirt pick-up by mortar and cement.

#### APPLICATION INFORMATION

#### **Application conditions**

Temperature between  $: 5 - 30^{\circ}\text{C}$ Relative humidity maximum : 85%

#### **Application methods**

Ready for use after thorough stirring

#### Brush:

Thinner : Do not thin Viscosity : Ready for use

#### Cleaning of equipment

Clean the brushes and equipment immediately after use with a proprietary brush cleaner.

## Advised layer thickness At 20°C/65% RH

Dry: Approx. 10 microns per coat

Wet: Approx. 36 microns

A Cetol HLS plus system should have a minimum dry film thickness of 20 microns.

The first layer strongly penetrates into the wood, securing adhesion, but not significantly adding to the total dry film thickness.

### Theoretical coverage

Dry layer thickness 10 microns, approx. 11 – 14 m<sup>2</sup>/Litre.

#### **Practical coverage**

Dry layer thickness 10 microns, approx. 10 – 14 m<sup>2</sup>/Litre.

Coverage greatly depends on the wood species under treatment, the surface condition, the method of application and conditions during application. On rough sawn timber the coverage is significantly lower (e.g. 7 - 10 m2/L).

#### **HEALTH & SAFETY INFORMATION**

Always read full Health, Safety & Environmental Information on can before use. Safety datasheet is available free on request.

#### ADDITIONAL INFORMATION

Product available in ready mixed and tinted colours.

Packaging size
Shelf life
Storage conditions

1 L, 2.5 L, 5 L

Minimum 24 months in original and unopened packaging, Stored in dry warehouse at temperatures between  $5 - 30^{\circ}$ C

The effectiveness of our product and systems is based on years of practical experience and research in our laboratories. We guarantee that the quality of the work on which our products are used meets the qualifications (Akzo Nobel Decorative Coatings bv) has promised, provided that all instructions given by us are correctly followed and the work has been carried out according to good craftsmanship. In case the end result has been influenced negatively by circumstances beyond our control, any and all liability are expressly excluded and disclaimed. Purchaser needs to check whether the delivered products are fit for the intended use. As soon as a new version of this (technical data sheet) is available, this one will no longer be valid.